

Seamles**SEAL**[™] ULTRA HSLV

Silicone Coating

Overview

SeamlesSEAL ULTRA HSLV is a single-component, moisture-cured, fluid-applied silicone coating that is specially formulated to meet low-VOC requirements. Once cured, the silicone coating membrane offers excellent resistance to water intrusion, UV exposure, and natural weathering. This product is designed to provide protection for a wide range of building surfaces. It is excellent for waterproofing and restoring existing roof systems, as well as for weather protection of SPF roofing systems.

Features and Benefits

- Superior leak protection
- Easy to apply and wide application window
- Weatherability
- Long-lasting
- Resistance to ponding water

Coverage Rate

SeamlesSEAL ULTRA HSLV Silicone Coating is 93% solids by volume. A typical application rate of 1.0-1.5 gallons per 100 square feet should yield a dry film thickness of approximately 15 mils in one coat. Waste, wind loss, and other variables will affect the actual dry film thickness.

Installation

1. All surfaces to be coated must be clean, dry, sound, and paintable. It may be necessary to power wash and/or prime to enhance adhesion.
2. No thinning or reducing is recommended. Mix well before using.
3. It is not recommended that this product be applied at temperatures below 40°F (4°C) or if inclement weather is expected within 1 hour of application.

4. This product is suitable for application through airless spray equipment or with a roller, squeegee, or brush. Utilize a pump with a minimum output of 3 gallons per minute and 3,500 psi fluid pressure capability, fed with a 5:1 transfer pump and with ½" and ¾" ID hose. Always use components rated for the pump maximum pressure. Use a 30-mesh screen or larger. Use a spray tip with a minimum orifice of .30" and 50 degree fan angle. Medium to heavy nap roller pads are recommended. Use hoses dedicated for silicone coatings.
5. This coating can be installed in one or multiple coats.
6. SPF should be coated within 24 hours of application. Subsequent coats should be applied within 24 hours of prior applications to ensure full and uniform adhesion. Coating must be evenly applied and pinhole free. The coating will cure in 2 to 8 hours, dependent on weather conditions such as temperature and humidity. Do not install additional coats until coating is fully cured.
7. Approved roofing granules may be installed in the topcoat to improve aesthetics, traffic resistance, and impact resistance.
8. See listing at www.nsf.org for application and cure instructions for rainwater catchment use.
9. Cleanup of spray equipment containing uncured material may be accomplished by flushing with VM&P Naphtha or Rule 66 mineral spirits. SeamlesSEAL ULTRA HSLV cures by reacting with moisture and should not be left in spray guns, pump equipment, or hoses for prolonged periods unless equipment contains moisture lock hoses, fittings, and seals. Equipment without these components will transmit sufficient moisture vapor to gradually form cured material on hose walls and at unsealed connections.

Review Carlisle Roof Foam and Coatings' specifications and details for complete installation information. Please contact CRFC for more information.

Precautions

- Not recommended for continuous immersion service, for use in cold storage applications without a vapor retarder, or directly over asphaltic surfaces without a sealer.
- Silicone coatings are slippery when wet. Exercise caution when walking on a roof under these conditions.
- Avoid breathing silicone vapors or spray mists. Use an appropriate MESA/NIOSH approved respirator when exposure can exceed recommended PEL. This product is not recommended for interior use. Additional care must be taken to prevent rooftop HVAC equipment from introducing silicone vapors into interior areas during application. Building occupants should be warned of spray operations in process.
- Keep cleaning solvents away from all sources of heat, sparks, flame, lighted smoking materials, or any other ignition source. Pumping equipment should be grounded to avoid accidental ignition due to static sparks.
- It is not recommended to store this material at temperatures exceeding 100°F (38°C). For maximum shelf life, store between 40°F and 70°F (4°C and 21°C). Higher temperatures will reduce shelf life.
- Remove any skin prior to mixing the material. Once container is opened, all product should be used. Container cannot be resealed without product skinning or curing inside container. Always keep covered and protected from the elements. When transporting this product, ensure that the lid is tight and the container is secured.
- See Safety Data Sheet (SDS) for complete safety information.

Ratings and Approvals

Underwriters Laboratories	File R26705
UL Evaluation Report	EX R26705
NSF Protocol P151 (white only)	
Cool Roof Rating Council Listed (white)	
FM Approved	
Title 24	Compliant
Meets Requirements of ASTM D6694 Standard Specification for Liquid-Applied Silicone Coating	
Texas Dept of Insurance RC476	
Miami Dade	NOA #20-0723.01 2/15/21
FL Product Approval	FL37994

Typical Properties and Characteristics

Property	Test Method	SeamlesSEAL ULTRA HSLV
Tensile Strength	ASTM D2370	244 psi @ 73°F (23°C)
		227 psi @ 0°F (-18°C)
Elongation	ASTM D2370	187% @ 73°F (23°C)
		121% @ 0°F (-18°C)
Tear Resistance	ASTM D624	24 lbf/in @ 73°F (23°C)
Permeance	ASTM E96 Procedure B	6.5 perms
Reflectivity	ASTM C1549	.87 initial/ .70 3 year aged (white)
Emissivity	ASTM C1371	.89 initial/ .90 3 year aged (white)
Solar Reflectance Index	ASTM E1980	SRI - White: 110
Water Absorption	ASTM D471	0.1 % @ 73°F (23°C)
Low Temp. Flexibility	ASTM D522 Procedure B	Pass @ -15°F (-26°C)
Weathering	ASTM G53	No degradation after 8,760 hours
Hardness	ASTM D2240	50 Shore A
Accelerated Weathering	ASTM D4798	5,000 hours pass
Max. Service Temp.		185°F (85°C)
Solids by Volume	ASTM D2697	93% +/- 2
Solids by Weight	ASTM D1644	96% +/- 2
Flash Point	ASTM D93	>105°F (41°C)
Cure Time		Min. 2 Hrs @ 100°F (38°C) & 90% RH, No metric values Max. 8-12 Hrs @ 40°F (4°C) & 20% RH, No metric values
VOC	EPA Method 24	<50 grams/L
Color		White, Light Gray, Dark Gray, Tan

Special colors are available at an additional charge with minimum order.

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

Shipping Information

Container Size	Gross Weight	Class
5-gallon pail (18.9 L)	60.5 lbs. (23 Kg)	55
50-gallon drum (189.3 L)	602 lbs.	55
250-gallon tote (946.4 L)	2933 lbs. (1330 Kg)	
D.O.T. Classification: BC - Roof Coating, Non-Regulated	Protect from freezing (32°F/0°C) during shipping and storage	



Sustainable. Seamless. Solutions.

100 Enterprise Drive • Cartersville, GA 30120 • 844.922.2355
www.CarlisleRFC.com